

# DAVID J HEFFER AND ASSOCIATES

Consulting Textile  
Technologists

djheffer@djha.com.au  
www.djha.com.au

22 Hicks Street, Lara, Vic, 3212  
Tel: (03) 5282 1337  
Fax: (03) 5282 1003  
ABN. 87 710 470 062



## LABORATORY REPORT

Date : 15 March 2021

Report Number: 216366C

Client: CHARLES PARSONS INTERIORS  
191-193 CLEVELAND STREET  
REDFERN NSW 2016

Reference: Laura Sampson

Sample: woven, Fenwick

Results:

Flammability (AS1530-1993 Part 2)

Direction	Speed factor (S)	Heat factor (H)	Spread factor (E)	Flammability index
warp	-	3	6	10
weft	-	3	7	

Note: The heat factor (H) will range from 0 upwards, the speed factor (S) from 0 to 60 and the spread factor (E) from 0 to 40. The value of the flammability index (I) will range from 0 to 100 for most materials.

DAVID J HEFFER  
DIRECTOR