

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing  
A.B.N 43 006 014 106


1st Floor, 191 Racecourse Road, Flemington, Victoria 3031  
P.O Box 240, North Melbourne, Victoria 3051  
Phone (03) 9371 2400

## TEST REPORT

**Client :** Charles Parsons & Co Pty Ltd  
Level 2  
191 - 193 Cleveland Street  
Redfern NSW 2016

**Test Number :** 25-001584  
**Issue Date :** 30/05/2025  
**Print Date :** 30/05/2025

**Sample Description** Clients Ref : "Jacquard Leaf Sheer"  
Sheer woven fabric with leaf pattern  
Colour : White  
End Use : Drapery  
Nominal Composition : 100% Polyester  
Nominal Mass per Unit Area/Density : 150g/m2



350630

76779

Page 1 of 2

© Australian Wool Testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing  
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Fiona McDonald

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)  
MANAGING DIRECTOR

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing  
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031  
P.O Box 240, North Melbourne, Victoria 3051  
Phone (03) 9371 2400

## TEST REPORT

**Client :** Charles Parsons & Co Pty Ltd  
Level 2  
191 - 193 Cleveland Street  
Redfern NSW 2016

**Test Number :** 25-001584  
**Issue Date :** 30/05/2025  
**Print Date :** 30/05/2025

**AS 1530.2-1993**

**Methods for Fire Tests on Building Materials, Components and Structures.  
Part 2: Test for Flammability of Materials**

Date Tested	30-05-2025	
Flammability Index	1	
	Length	Width
Spread Factor	0	0
Heat Factor	1	1
Maximum height (d)		
Mean	3.0	3.1
Coefficient of Variation	22.0	31.1 %
Heat (a)		
Mean	2.1	1.8 °C.min
Coefficient of Variation	10.4	27.3 %
Number of Specimens Tested	9	9

Tested as received.

These test results relate only to the behaviour of the test specimens of the material under the particular conditions of the test, and they are not intended to be the sole criterion for assessing the potential fire hazard of the material in use.

350630

76779

Page 2 of 2

© Australian Wool Testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing  
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Fiona McDonald

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)  
MANAGING DIRECTOR